Central Span[™]


Standing Seam Roof Panel



Preferred by architects for superior style and performance

Central Span is a mechanically-seamed metal panel. It has a standard flat pan with mild striations and a vertical rib, giving it an appearance often favored by traditional architects. Central Span roofs meet the requirements for a wide range of roof slopes, shapes, loads, weather, and related conditions.

- One of the highest uplift ratings in the industry.
- Factory applied sealant.
- Clip provides for thermal movement.
- 90° or 180° seam.



10274 W 600 South Mentone, IN 46539 574-353-7701 Fax: 574-353-7183



NIFFTONE.COM

Copyright © 2021, Central States Manufacturing, Inc., All Rights Reserved. Galvalume[®] is a registered trademark of BIEC International, Inc. C E FLYR_CentralSpan_230207.1

Choose an energy efficient finish.

Solar Reflectivity is the metal panel's ability to reflect sunlight. This characteristic of metal roofing is the most important in terms of energy savings. Cool metal roofing reflects much of the sun's rays, making the surface of the metal much cooler than material with a lower solar reflectivity rating.

Emissivity is the metal panel's ability to release absorbed heat. A low emissivity rating means the material will be hot to the touch (it doesn't release the heat), while material with a higher emissivity rating will be cooler to the touch. Therefore, metal with a low emissivity rating retains heat and may be more desirable for a cooler climate, while a high emissivity rating reflects heat and is more effective for saving energy in a warmer climate.

COLOR	INITIAL SOLAR REFLECTIVITY	INITIAL EMISSIVITY
Ash	0.32	0.83
Autumn	0.21	0.87
Brite	0.55	0.83
Bronze	0.25	0.83
Dark Bronze	0.25	0.83
Evergreen	0.27	0.85
Galvalume [®] (Acrylic Coated)	0.77	0.08
Sand	0.35	0.75
Slate Gray	0.18	0.87
Smoke	0.25	0.83
Terratone	0.32	0.83
Tudor	0.29	0.88
Verdigris	0.32	0.83

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. Laboratory and Exposure site are ISO 17025 Accredited, Laboratory is also EPA Accredited. Panels are unwashed. Values are correct at time of printing. Ratings may change as paint technologies change. Check our website for details.

Find more information at NIFFTONE.COM

MINIMUM SPECIFICATIONS FOR PRIME PAINTED PANELS

GAUGE 24 ga.

STEEL THICKNESS 0.023"

PAINT THICKNESS Top coat paint: .70 mil Top coat primer: .30 mil Bottom coat backer: .35 mil Bottom coat primer: .20 mil

TOTAL THICKNESS 0.02455"

RUST PROTECTANT SUBSTRATE Galvalume® AZ50

STEEL STRENGTH 50,000 PSI min

PAINT SYSTEM Fluropon®

WARRANTY

Lifetime limited paint adhesion 30-yr. chalk and fade 20-yr. Galvalume perforation

TESTING & APPROVALS

TESTING

	Air Leakage Test Through Exterior Metal Roof Panel Water Leakage Test of Exterior Metal Roof Panel
APPROVALS	
UL2218	UL Approval, Impact Resistance, Class 4
UL580	UL Approval, Uplift Resistance, Class 90
UL790	UL Approval,
RC-446	Fire Resistance, Class A Texas Windstorm Approval, 24 ga. Quad Lock,
RC-447	Over Steel Purlins Texas Windstorm Approval, 24 ga. Triple Lock,
FL17205	Over Steel Purlins Florida Approval, 16" wide, min 24 ga. Standing Seam
FL14016	Panel over open supports Florida Approval, 24 ga. Roof Panel Over Open Supports (NON-HVHZ)